



PoliXL™ PCM12BK

PC, Melt Index 12, Black

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Specific Gravity	1.20 g/cc	1.20 g/cc	D792
Water Absorption Equilibrium, 23 °C, 50% RH	0.15 %	0.15 %	D570
Melt Flow Rate (1.2kg, 300 °C)	12 g/10min	12 g/10min	D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Break)	9000 psi	62 MPa	D638
Tensile Strain (Break)	70 %	70 %	D638
Flexural Modulus	340000 psi	2340 MPa	D790
Flex Strength	14000 psi	95 MPa	D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength 23°C	15 ft-lb/in	80 kJ/m ²	D256

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature 0.45 Mpa, Unannealed 1.8 MPa Unannealed	275 °F 266 °F	135 °C 130 °C	ISO 75
Glass Transition Temperature	293 °F	145 °C	DSC

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
0.750 mm	V-2	V-2	UL94
2.00 mm	V-2	V-2	UL94
4.00 mm	V-1	V-1	UL94



Legal Disclaimer

The information presented here is accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. Our products are sold with the express understanding that our customers will conduct their own tests to determine the suitability of the material for their particular use. Nothing herein shall be construed as permission or recommendation to practice a patented invention without a license. The sole liability for Niche Polymer for any claims arising out of the manufacturer, use or sale of its products shall be for our customers purchase price or material replacement.

