



PolixL™ PPHGF30N

PPH, 30% Fiberglass Reinforced, Natural

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Specific Gravity	1.15 g/cc	1.15 g/cc	D792
Mold Shrinkage Parallel: 23 °C Perpendicular: 23°C	0.1-0.6% 0.5-1.2%	0.1-0.6% 0.5-1.2%	D955
Melt Flow Rate (2.16kg, 230 °C)	15 g/10min	15g/ 10min	D1238
Ash (Glass-fiber)	30 %	30%	D2584

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Break)	11,000 psi	76 MPa	ISO 527
Tensile Strain (Break)	3 %	3%	ISO 527
Flexural Modulus	800,000psi	5,515 MPa	ISO 178
Flex Strength	15,000 psi	103 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength 23 °C	1.7 ft-lb/in	9 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 23°C	10 ft-lb/in	54 kJ/m ²	ISO 179
Notched Izod Impact Strength 23°C	1.5 ft-lb/in	8 kJ/m ²	ISO 180

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature 0.45 MPa Unannealed 1.8 MPa Unannealed	- 284 °F	- 140 °C	ISO 75
Melting Temperature	324 °F	162 °C	ISO 11357

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
0.71 mm	HB	HB	UL94
1.50 mm	HB	HB	UL94
3.00 mm	HB	HB	UL94



Legal Disclaimer

The information presented here is accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. Our products are sold with the express understanding that our customers will conduct their own tests to determine the suitability of the material for their particular use. Nothing herein shall be construed as permission or recommendation to practice a patented invention without a license. The sole liability for Niche Polymer for any claims arising out of the manufacturer, use or sale of its products shall be for our customers purchase price or material replacement.

